## **PRODUCT INFORMATION**

## DuPont<sup>™</sup> Hytrel<sup>®</sup> 30HS THERMOPLASTIC POLYESTER ELASTOMER

## Product Information

Common features of Hytrel® thermoplastic polyester elastomer include mechanical and physical properties such as exceptional toughness and resilience, high resistance to creep, impact and flex fatigue, flexibility at low temperatures and good retention of properties at elevated temperatures. In addition, it resists many industrial chemicals, oils and solvents. Special grades include heat stabilised, flame retardant, food contact compliant, blow molding and extrusion grades. Concentrates offered include black pigments, UV protection additives, heat stabilisers, and flame retardants.

Hytrel® thermoplastic polyester elastomer is plasticiser free.

The good melt stability of Hytrel® thermoplastic polyester elastomer normally enables the recycling of properly handled production waste. If recycling is not possible, DuPont recommends, as the preferred option, incineration with energy recovery (-24 kJ/g of base polymer) in appropriately equipped installations. For disposal, local regulations have to be observed.

Hytrel® thermoplastic polyester elastomer typically is used in demanding applications in the automotive, fluid power, electrical/electronic, consumer goods, appliance and power tool, sporting goods, furniture, industrial and off-road transportation/equipment industry.

## HYTREL® 30HS is a heat stabilizer concentrate for use in Hytrel® thermoplastic polyester elastomer. It contains a discolouring antioxidant. It is not suited for light-colored finished products.

General information	Value	Unit	Test Standard
Resin Identification	PA+TPC-ET	-	ISO 1043
Part Marking Code	PA+TPC-ET	-	ISO 11469
Thermal properties	Value	Unit	Test Standard
Melting temperature, 18°F/min	155	°C	ISO 11357-1/-3
Flammability	Value	Unit	Test Standard
FMVSS Class	В	-	ISO 3795 (FMVSS 302)
Burning rate, Thickness 1 mm	<100	mm/min	ISO 3795 (FMVSS 302)
Other properties	Value	Unit	Test Standard
Density	1100	kg/m³	ISO 1183
		_	

haracteristics.					
Delivery form	Pellets				
Special characteristics	<ul> <li>Heat stabilized or stable to heat</li> </ul>				
Regional Availability	<ul><li>North America</li><li>Europe</li></ul>	<ul><li>Asia Pacific</li><li>South and Central America</li></ul>	<ul><li>Near East/Africa</li><li>Global</li></ul>		

Contact DuPont for Material Safety Data Sheet, general guides and/or additional information about ventilation, handling, purging, drying, etc. ISO Mechanical properties measured at 160 mil (Hytrel® measured at 80 mil), IEC Electrical properties measured at 80 mil, all ASTM properties measured at 120 mil, and test temperatures are 73°F unless otherwise stated.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents. Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer representative and read Medical Caution H-50103-5.

Copyright © 2017 DuPont or its affiliates. All Rights Reserved. The DuPont Oval Logo, DuPont<sup>M</sup>, The miracles of science<sup>M</sup> and all products denoted with  $\mathbb{B}$  or <sup>M</sup> are registered trademarks or trademarks of E.I. du Pont de Nemours and Company or its affiliates.

Revised: 2016-09-20

Page: 1 of 1

To find out more, visit DuPont Performance Polymers or contact nearest DuPont location.

North America Tel: +1 302 999-4592 Toll-Free (USA): 800 441-0575 **Asia Pacific** Tel: +81 3 5521 8600 Europe/Middle East/Africa Tel: +41 22 717 51 11



Copyright 2017 DuPont. The DuPont Oval Logo is a trademark or registered trademark of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.